

CDA 681

Bronze Brazing Alloy

NOMINAL COMPOSITION

Copper	58.0% ± 2.0%
Zinc	Remainder
Iron	0.75% ± 0.45%
Tin	0.95% ± 0.15%
Manganese	0.01% - 0.50%
Lead	0.05%
Aluminum	0.01%
Silicon	0.04% - 0.15%
Other Elements (Total)	0.50% Max

PHYSICAL PROPERTIES

Color	Brass Yellow
Melting Point (Solidus)	1590°F (866°C)
Flow Point (Liquidus)	1630°F (888°C)
Brazing Temperature Range	1670°F - 1750°F (910°C - 954°C)
Specific Gravity	8.07
Density (Lbs /in ³)	0.292
Electrical Conductivity (% IACS) ⁽¹⁾	24.0
Electrical Resistivity (Microhm-cm)	7.18

⁽¹⁾ IACS = International Annealed Copper Standard

PRODUCT USES

CDA 681 is a low fuming bronze filler metal used for brazing of ferrous and non-ferrous alloys such as steel and copper. This alloy is typically used where close fit up cannot be maintained and high brazing temperatures are permissible.

BRAZING CHARACTERISTICS

CDA 681 has good wetting characteristics on ferrous and non-ferrous materials, particularly steels and coppers. Maximum strength and joint integrity are obtained where joint clearance falls within the range of 0.003 in. - 0.005 in. per side. Handy[®] Flux Hi-Temp should be used in conjunction with this alloy. Heating methods include torch, induction, and furnace.

PROPERTIES OF BRAZED JOINTS

The properties of a brazed joint are dependent upon numerous factors including base metal properties, joint design, metallurgical interaction between the base metal and the filler metal.

AVAILABLE FORMS

Wire, strip, engineered preforms, specialty preforms per customer specification, powder and paste.

SPECIFICATIONS

CDA 681 alloy conforms to the following specifications:

- Unified Numbering System (UNS) C68100
- American Welding Society (AWS) A5.8/A5.8M RBCuZn-C

APPLICABLE PRODUCT CODE(S)

The applicable Lucas-Milhaupt product code(s) for this technical data sheet: 60-681, CDA681.

SAFETY INFORMATION

The operation and maintenance of brazing equipment or facility should conform to the provisions of American National Standard (ANSI) Z49.1, "Safety in Welding and Cutting". For more complete information refer to the Material Safety Data Sheet for CDA 681.

WARRANTY CLAUSE

Lucas-Milhaupt, Inc. believes the information contained herein to be reliable. However, the information is given by Lucas-Milhaupt, Inc. without charge and the user shall use such information at its own discretion and risk. This information is provided on an "AS IS" AND "AS AVAILABLE" basis and Lucas-Milhaupt, Inc. specifically disclaims warranties of any kind, either express or implied, including, but not limited to, warranties of title or implied warranties of merchantability or fitness for a particular purpose. No oral advice or written or electronically delivered information given by Lucas-Milhaupt, Inc. or any of its officers, directors, employees, or agents shall create any warranty. Lucas-Milhaupt, Inc. assumes no responsibility for results obtained or damages incurred from the use of such information in whole or in part.