

## HI-TEMP® 852

### ***NOMINAL COMPOSITION***

---

Nickel	Remainder
Chromium	29.5% ± 2.0%
Phosphorous	6.0% ± 0.4%
Silicon	4.0% ± 0.2%
Boron	0.01% Max
Iron	0.20% Max
Carbon	0.03% Max
Sulfur	0.02% Max
Titanium	0.05% Max
Aluminum	0.05% Max
Zirconium	0.05% Max
Oxygen	0.03% Max
Selenium	0.005% Max
Cadmium	0.01% Max
Lead	0.025% Max
Other Elements (Total)	0.50% Max

### ***PHYSICAL PROPERTIES***

---

Color	Iron Gray
Melting Point (Solidus)	1778°F (970°C)
Flow Point (Liquidus)	1886°F (1030°C)
Brazing Temperature Range	1922°F - 2012°F (1050°C - 1100°C)
Density (Lbs/in <sup>3</sup> )	.227
Electrical Conductivity (%IACS) <sup>(1)</sup>	N/A
Electrical Resistivity (Microhm-cm)	N/A

<sup>(1)</sup> IACS = International Annealed Copper Standard

### ***PRODUCT USES***

---

Hi-Temp 852 is a nickel-chromium-silicon brazing alloy powder used in high temperature strength and oxidation applications. Typically this alloy is used for joining super alloys, corrosion and heat resistant steels, and alloys requiring good joint strength at high temperatures while maintaining good corrosion and oxidation resistant characteristics. Typical applications would include structural members in jet engines, turbines, EGR coolers, and other severe conditions.

### ***BRAZING CHARACTERISTICS***

---

Hi-Temp 852 has a wide melting range between its flow point and melting point, thus fast heating should be employed to avoid liquation. To achieve maximum flow, strength and joint ductility in furnace brazing, it is recommended to maintain a brazing temperature closer to 2012°F(1100°C). To avoid diffusion and erosion, brazing temperatures closer to 1922°F (1050°C) are preferred. In atmosphere brazing, base metals containing more than 0.5% aluminum and/or titanium (i.e. Inconel X and A286) are often nickel-plated (0.0005 in. to 0.0015 in. thick depending upon brazing temperature and cycle), if difficulties in wetting and bonding are encountered. On thinner sections or less ductile base metals, brazing should be done at the low end of the brazing range with small clearances, fast heating/cooling cycles, and a minimum quantity of brazing alloy to minimize erosion.

## ***PROPERTIES OF BRAZED JOINTS***

---

The properties of a brazed joint are dependent upon numerous factors including base metal properties, joint design, metallurgical interaction between the base metal and the filler metal. Joint ductility, strength and high temperature properties, and alloy re-melt temperature increase with increasing temperature and heating cycles, and decreasing joint clearances. Oxidation tests on Inconel for 500 hours in still air at 2200°F (1204°C) showed no deteriorations of fillet. Satisfactory corrosion resistance to liquid alkali metals (Na, K) and high temperature water were obtained in independent tests on Inconel and stainless steel.

## ***AVAILABLE FORMS***

---

Powder

## ***SPECIFICATIONS***

---

Hi-Temp 852 alloy conforms to the following specifications: N/A

## ***APPLICABLE PRODUCT CODE(S)***

---

The applicable Lucas-Milhaupt product code(s) for this technical data sheet: 77-852.

## ***SAFETY INFORMATION***

---

The operation and maintenance of brazing equipment or facility should conform to the provisions of American National Standard (ANSI) Z49.1, "Safety in Welding and Cutting". For more complete information refer to the Material Safety Data Sheet for Hi-Temp 852.

## ***WARRANTY CLAUSE***

---

Lucas-Milhaupt, Inc. believes the information contained herein to be reliable. However, the information is given by Lucas-Milhaupt, Inc. without charge and the user shall use such information at its own discretion and risk. This information is provided on an "AS IS" AND "AS AVAILABLE" basis and Lucas-Milhaupt, Inc. specifically disclaims warranties of any kind, either express or implied, including, but not limited to, warranties of title or implied warranties of merchantability or fitness for a particular purpose. No oral advice or written or electronically delivered information given by Lucas-Milhaupt, Inc. or any of its officers, directors, employees, or agents shall create any warranty. Lucas-Milhaupt, Inc. assumes no responsibility for results obtained or damages incurred from the use of such information in whole or in part.