

LTB4241SSKNC

NOMINAL COMPOSITION

Aluminum	Remainder
Silicon	10.0% ± 1.0%
Copper	0.30% Max
Magnesium	0.05% Max
Iron	0.8% Max
Zinc	0.10% Max
Manganese	0.05% Max
Titanium	0.20% Max
Other Elements (Each)	0.05% Max
Other Elements (Total)	0.15% Max

PHYSICAL PROPERTIES

Color	Grayish-White
Melting Point (Solidus)	1070°F (577°C)
Flow Point (Liquidus)	1095°F (591°C)
Brazing Range	1095°F - 1120°F (591°C - 604°C)

PRODUCT USES

LTB4241SSKNC paste is a stable mixture of aluminum/silicon filler metal and NOCOLOK[®] flux, a non-corrosive flux patented by Alcan International Ltd. The paste can be used in furnace, torch or induction brazing processes for joining a wide variety of aluminum alloys. No post braze cleaning operations are required. The flux and its residues are non-hygroscopic and non-corrosive.

LTB4241SSKNC paste is a premixed brazing paste adjusted to a stable dispensing viscosity for all automatic and hand dispensers. If necessary, stir before using to insure proper consistency. Lucas-Milhaupt, Inc. brazing paste can be thinned with alcohol.

The optimum filler metal to flux ratio depends on brazing atmosphere and heating rate. Lucas-Milhaupt, Inc. will blend special mixes for each customer's unique brazing operation.

PROPERTIES OF BRAZED JOINTS

The properties of a brazed joint are dependent upon numerous factors including base metal properties, joint design, metallurgical interaction between the base metal and the filler metal. Joint clearances of 0.003 - 0.006 in. (0.076 - 0.152 mm) per side are optimum for achieving highest joint strength. Joints with increased clearances can still produce adequate joint strengths depending on final operating conditions.

POST CLEANING

LTB4241SSKNC paste contains a noncorrosive flux and requires no post braze cleaning operation; however, if it is desired to remove the residue, a 50/50 mixture of nitric acid and distilled water will remove residue. Agitate the part in the solution for 30 seconds to remove all flux.

WARRANTY & STORAGE

Lucas-Milhaupt, Inc. warrants their Brazing and Soldering Paste products for 90 days from the date of shipment if stored in the original unopened container. Optimal storage conditions would be 65°F (18°C) - 75°F (24°C), clean and dry. It is recommended that the paste products are stored away from direct heat. Paste may require mixing to regain a homogenous mixture before application.

The 90 day warranty should not be interpreted as the shelf or useful life of the product. The paste products may be used well beyond the 90 day warranty, unless customer testing or production results indicate unsatisfactory performance of the product.

AVAILABLE PACKAGING

LTB4241SSKNC aluminum brazing paste is available in various size syringes, jars and cartridges.

SPECIFICATIONS

Aluminum powder chemistry is manufactured in accordance to the following specifications:

- AWS A5.8 (BA1Si-5)
- QQ-B-655 (FS-BA1Si-5)
- Alcoa 714
- AA 4045

APPLICABLE PRODUCT CODE(S)

The applicable Lucas-Milhaupt product code(s) for this technical data sheet: 84-368.

SAFETY INFORMATION

The operation and maintenance of brazing equipment or facility should conform to the provisions of American National Standard (ANSI) Z49.1, "Safety in Welding and Cutting". For more complete information refer to the Material Safety Data Sheet for LTB4200SSKNC.

WARRANTY CLAUSE

Lucas-Milhaupt, Inc. believes the information contained herein to be reliable. However, the information is given by Lucas-Milhaupt, Inc. without charge and the user shall use such information at its own discretion and risk. This information is provided on an "AS IS" AND "AS AVAILABLE" basis and Lucas-Milhaupt, Inc. specifically disclaims warranties of any kind, either express or implied, including, but not limited to, warranties of title or implied warranties of merchantability or fitness for a particular purpose. No oral advice or written or electronically delivered information given by Lucas-Milhaupt, Inc. or any of its officers, directors, employees, or agents shall create any warranty. Lucas-Milhaupt, Inc. assumes no responsibility for results obtained or damages incurred from the use of such information in whole or in part.