

SILVALOY® 495 (BRAZE™ 495, SILVALOY® A49NM)

NOMINAL COMPOSITION

Silver	49.0% ± 1.0%
Copper	16.0% ± 1.0%
Zinc	23.0% ± 2.0%
Manganese	7.5% ± 0.5%
Nickel	4.5% ± 0.5%
Other Elements (Total)	0.15% Max

PHYSICAL PROPERTIES

Color	Yellow White
Melting Point (Solidus)	1260°F (682°C)
Flow Point (Liquidus)	1290°F (699°C)
Brazing Temperature Range	1290°F - 1500°F (699°C - 815°C)
Specific Gravity	8.93
Density (Troy oz/in ³)	4.71
Electrical Conductivity (%IACS) ⁽¹⁾	5.70
Electrical Resistivity (Microhm-cm)	30.3

⁽¹⁾ IACS = International Annealed Copper Standard

PRODUCT USES

Because of its excellent wetting properties, Silvaloy 495 is used extensively for brazing tungsten carbide inserts to cutting tools and rock drills. It may be used for joining all types of stainless steels and carbon steels.

BRAZING CHARACTERISTICS

Silvaloy 495 is a cadmium-free, low temperature brazing filler metal used for brazing of tungsten carbides, steels and stainless steels. Because of its high manganese content, Silvaloy 495 may tend to liquate (i.e. separate into low and high melting constituents). However, this can be mitigated by rapidly heating the joint assembly through the melting range of the Silvaloy 495. Handy® Flux may be used with Silvaloy 495, but on some of the more difficult to braze alloys, such as carbides and stainless steels, Handy® Flux Type B-1 assists in producing better wetting of the joint surfaces.

PROPERTIES OF BRAZED JOINTS

The properties of a brazed joint are dependent upon numerous factors including base metal properties, joint design, metallurgical interaction between the base metal and the filler metal. Butt joints in the listed metals at room temperature indicate the following typical results:

	Tensile Strength (lbs/in ²)	Elongation (% in 2 in.)
1020 Carbon Steel	49,000	4.00
1095 Carbon Steel	92,400	7.00
304 Stainless Steel	76,600	15.0

AVAILABLE FORMS

Wire, strip, engineered preforms, specialty preforms per customer specification, powder and paste.

SPECIFICATIONS

Silvaloy 495 alloy conforms to the following specifications:

- American Welding Society (AWS) A5.8/A5.8M BAg-22
- ASME Boiler & Pressure Vessel Code, Sec II-C, SFA-5.8 BAg-22
- Federal Specification QQ-B-654 BAg-22

APPLICABLE PRODUCT CODE(S)

The applicable Lucas-Milhaupt product code(s) for this technical data sheet: 32-495, 35535.

SAFETY INFORMATION

The operation and maintenance of brazing equipment or facility should conform to the provisions of American National Standard (ANSI) Z49.1, "Safety in Welding and Cutting". For more complete information refer to the Material Safety Data Sheet for Silvaloy 495.

WARRANTY CLAUSE

Lucas-Milhaupt, Inc. believes the information contained herein to be reliable. However, the information is given by Lucas-Milhaupt, Inc. without charge and the user shall use such information at its own discretion and risk. This information is provided on an "AS IS" AND "AS AVAILABLE" basis and Lucas-Milhaupt, Inc. specifically disclaims warranties of any kind, either express or implied, including, but not limited to, warranties of title or implied warranties of merchantability or fitness for a particular purpose. No oral advice or written or electronically delivered information given by Lucas-Milhaupt, Inc. or any of its officers, directors, employees, or agents shall create any warranty. Lucas-Milhaupt, Inc. assumes no responsibility for results obtained or damages incurred from the use of such information in whole or in part.