

## SILVALOY 697 (LM 27-697 VTG <sup>(1)</sup>)

### ***NOMINAL COMPOSITION***

---

Silver	68.7% -70.7%
Copper	Remainder
Germanium	1.75% - 2.25%
Cobalt	0.3% ± 0.1%
Zinc	0.001% Max
Phosphorous	0.002% Max
Carbon	0.005% Max
Lead	0.002% Max
Other volatile elements <sup>(2)</sup>	0.001% Max
Volatile elements total (incl. Cd, Zn, Pb)	0.010% Max
Total non-volatile elements	0.05% Max

<sup>(1)</sup> Vacuum Tube Grade

<sup>(2)</sup> Elements with a vapor pressure higher than  $10^{-7}$  torr at 932°F (500°C) such as Mg, Sb, K, Na, Li, Ti, S, Cs, Rb, Se, Te, Sr, and Ca

### ***PHYSICAL PROPERTIES***

---

Color	Silver White
Melting Point (Solidus)	1435°F (780°C)
Flow Point (Liquidus)	1435°F (780°C)
Brazing Temperature Range	1465°F - 1650°F (795°C - 900°C)
Specific Gravity	9.82
Density (Troy oz/in <sup>3</sup> )	5.17
Electrical Conductivity (% IACS) <sup>(3)</sup>	N/A
Electrical Resistivity (Microhm-cm)	N/A

<sup>(3)</sup> IACS = International Annealed Copper Standard

### ***PRODUCT USES***

---

Silvaloy 697 (VTG) can be used in all types of moderate temperature vacuum systems in particular brazing of the vacuum tube assemblies in a one step braze process. This alloy is generally used to braze copper, nickel, copper-nickel alloys and stainless steel alloys in a vacuum environment without the necessity of plating of stainless steel substrates.

### ***BRAZING CHARACTERISTICS***

---

Silvaloy 697 is a modified silver-copper eutectic filler metal with small additions of cobalt and germanium. On either silver, nickel, or copper base alloys Silvaloy 697 may exhibit a decrease in fluidity and an increase in re-melt temperature, after brazing if some solution of base metal occurs in the filler metal. The properties of a brazed joint are dependent upon numerous factors including base metal properties, joint design, metallurgical interaction between the base metal and the filler metal.

### ***AVAILABLE FORMS***

---

Wire, strip, engineered preforms, specialty preforms per customer specification.

## ***SPECIFICATIONS***

---

Silvaloy 697 (VTG) conforms to the following specifications: N/A

## ***APPLICABLE PRODUCT CODE(S)***

---

The applicable Lucas-Milhaupt product code(s) for this technical data sheet: A00000307, Legacy Code: 27-697.

## ***SAFETY INFORMATION***

---

The operation and maintenance of brazing equipment or facility should conform to the provisions of American National Standard (ANSI) Z49.1, "Safety in Welding and Cutting". For more complete information refer to the Material Safety Data Sheet for Silvaloy 697 (VTG).

## ***WARRANTY CLAUSE***

---

Lucas-Milhaupt, Inc. believes the information contained herein to be reliable. However, the information is given by Lucas-Milhaupt, Inc. without charge and the user shall use such information at its own discretion and risk. This information is provided on an "AS IS" AND "AS AVAILABLE" basis and Lucas-Milhaupt, Inc. specifically disclaims warranties of any kind, either express or implied, including, but not limited to, warranties of title or implied warranties of merchantability or fitness for a particular purpose. No oral advice or written or electronically delivered information given by Lucas-Milhaupt, Inc. or any of its officers, directors, employees, or agents shall create any warranty. Lucas-Milhaupt, Inc. assumes no responsibility for results obtained or damages incurred from the use of such information in whole or in part.