

TRIMET® 259 **(PLYMETAL® A50N)**

NOMINAL COMPOSITION

Braze Filler Metal: Silvaloy 505 (Clad Portion)

Silver	50.0% ± 1.0%
Copper	20.0% ± 1.0%
Zinc	28.0% ± 2.0%
Nickel	2.0% ± 0.5%
Other Elements (Total)	0.15% Max

Core

Copper	99.90% Min
--------	------------

PHYSICAL PROPERTIES

Braze Filler Metal: Silvaloy 505 (Clad Portion)

Melting Point (Solidus)	1220°F (660°C)
Flow Point (Liquidus)	1305°F (705°C)
Brazing Temperature Range	1305°F - 1550°F (705°C - 843°C)

PRODUCT USES

Trimet 259 is a three layer composite metal sandwich consisting of a copper core clad on each side with Silvaloy 505 alloy. The relative thicknesses of the three (3) layers are in a 1/2/1 ratio. Other relative thickness ratios can be produced for special applications if warranted.

Trimet 259 is useful for brazing large carbide tools inserts with braze surface areas in excess of 0.5 in² (322.58 mm²) or linear dimension over 0.75 in (19mm). In these cases the stress normally set up in the carbide, by differential contraction between the carbide and tool shank during cooling, is relieved by the yielding of the copper core of the Trimet 259. This product is used as pre-placed shim at the interface of the parts being joined. Brazing procedures are identical with those required for Silvaloy 505.

Trimet is sometimes used to braze aluminum-bronze to steel. The copper acts as a barrier layer to prevent migration of aluminum from aluminum-bronze base metal to the steel surface and adversely affecting the wetting of the steel by the Silvaloy 505.

Trimet shims have also found use in joining porous sintered parts and wire mesh screens where “wicking” of the filler metal is normally challenging. The copper core in these cases acts to restrict filler metal flow, confining it to the joint area where needed.

AVAILABLE FORMS

Strip, engineered preforms, specialty preforms per customer specification.

SPECIFICATIONS

Silvaloy 505 alloy conforms to the following specifications:

- American Welding Society (AWS) A5.8/A5.8M BAg-24
- ASME Boiler & Pressure Vessel Code, Sec II-C, SFA-5.8 BAg-24

APPLICABLE PRODUCT CODE(S)

The applicable Lucas-Milhaupt product code(s) for this technical data sheet: 38-259, ESP1A.

SAFETY INFORMATION

The operation and maintenance of brazing equipment or facility should conform to the provisions of American National Standard (ANSI) Z49.1, "Safety in Welding and Cutting". For more complete information refer to the Material Safety Data Sheet for Trimet 259.

WARRANTY CLAUSE

Lucas-Milhaupt, Inc. believes the information contained herein to be reliable. However, the information is given by Lucas-Milhaupt, Inc. without charge and the user shall use such information at its own discretion and risk. This information is provided on an "AS IS" AND "AS AVAILABLE" basis and Lucas-Milhaupt, Inc. specifically disclaims warranties of any kind, either express or implied, including, but not limited to, warranties of title or implied warranties of merchantability or fitness for a particular purpose. No oral advice or written or electronically delivered information given by Lucas-Milhaupt, Inc. or any of its officers, directors, employees, or agents shall create any warranty. Lucas-Milhaupt, Inc. assumes no responsibility for results obtained or damages incurred from the use of such information in whole or in part.